

**ATTAR TEST REPORT NUMBER: 14/8242.2**

The results of the tests, calibrations and/or measurements included in this document are traceable to Australian/national standards.
Accredited for compliance with ISO/IEC 17025.
Accreditation Number: 2735

12 September 2014

Total Pages: 2**OIL-WET INCLINING PLATFORM SLIP RESISTANCE**

Job No: M14/8242

Prepared for:	Mirotone Pty Ltd 21 Marigold Street REVESBY NSW 2212	
Attention:	Ian McGregor	
Test Site:	ATTAR, Unit 1, 64 Bridge Road, Keysborough.	
Test Date:	10 September 2014	
Manufacturer:	Unknown	
Test Specimen, Size & Quantity:	One coat FASTASEAL 3030 Clear Sealer. One coat TITAN GLOSS. One coat TITAN GLOSS containing Polycure 3920 High Grip applied to timber board. 1000x500 mm, 1 off supplied, Refer to Figure 1.	
Sampling & Direction of Testing:	Sampling conducted by client. Test conducted parallel with grain of timber.	
Test Personnel:	Marcus Braché & Daniel King	
Preparation:	Washed with pH neutral detergent, rinsed with water, then dried.	
Joint Width:	N/A	
Air Temperature:	22°C	
Test Standard:	AS 4586 - 2013 Slip resistance classification of new pedestrian surface materials – Appendix D.	
Surface Structure :	Structured	
Test Shoes:	Lupos Picasso	
Classification Criteria: (TABLE 5 in AS 4586 - 2013)	Classification	Angle, degrees
	No Classification	<6
	R9	≥6<10
	R10	≥10<19
	R11	≥19<27
	R12	≥27<35
	R13	≥35
Displacement Space:	Not Measured	
Displacement Space Assessment Group:	N/A	
Corrected Mean Overall Acceptance Angle (rounded down to the nearest degree):	23°	
Classification:	R11	

These results apply only to the specimens tested and it is recommended that before selection of flooring or paving materials the effect of service conditions, including maintenance procedures and wear on their slip-resistance be checked.

NOTE: Any specimens supplied will be disposed of in two (2) months time, unless otherwise instructed.

ATTAR

Marcus Braché
Senior Engineering Technician
Approved Signatory

This report may not be reproduced except in its entirety.

Page 1 of 2

ATTAR - Advanced Technology Testing and Research
A division of Engineering Materials Evaluation Pty Ltd ABN 14 006 554 785

Unit 1, 64 Bridge Road, Keysborough Victoria 3173 T (03) 9574 6144 F (03) 9574 6133 E admin@attar.com.au www.attar.com.au



Figure 1: One coat FASTASEAL 3030 Clear Sealer. One coat TITAN GLOSS. One coat TITAN GLOSS containing Polycure 3920 High Grip applied to timber board.