

## TITAN Fast Sealer

TITAN Fast Sealer is an economical, single pack, fast drying sealer designed to be used as a first coat over raw timber and cork flooring.

### Product Advantages

- Fast drying
- Easy sanding

### Typical Applications

Interior use only. Timber, parquetry, particleboard or cork flooring.

*Not suitable for exterior or wet area applications e.g. bathrooms or around swimming pools.*

*Caution: floor will be slippery when wet.*

### Product Properties

Build: Good  
Sandability: Excellent  
Levelling & Flow: Excellent

### Typical Properties

Colour: Milky in can. Dries clear  
Gloss: Sealer

### Coverage:

Timber, Parquetry Floors – 12-15 m<sup>2</sup> per litre  
Cork & Particleboard – coverage will be reduced.

Coverage is dependent upon the porosity of the substrate.

### Thinning:

Not normally required but, if desired, add up to 5% Thinners 3310 or in hot weather add up to 3% Wet Edge Extender 3320.

### Application Methods:

Equipment: 6mm mohair roller and high quality brush

Preparing the floor to a professional standard is essential to achieve the best results.

- Fill all nail holes with a water based putty, allow to dry.
- Sand uncoated floor with 120-150 grade sandpaper or screenback on a flexible pad to ensure floor is uniformly dull with no sanding scratches, nibs or fur. Vacuum thoroughly to ensure all sanding dust is removed. Take care to avoid scratching the surface.
- Apply a liberal first coat of TITAN Fast Sealer using a 6mm mohair roller and good quality brush to cut in. Allow to dry for 45 minutes.
- Sand floor with 150-180 grade sandpaper or screenback, remove all nibs, fluff and fur. Vacuum all dust.
- Apply a coat of TITAN Gloss. Allow to dry per instructions on the data sheet.
- Thoroughly sand floor with 150-180 grade sandpaper or screenback, remove all nibs, fluff and fur. Vacuum all dust.
- Apply the final coat of TITAN Gloss (per data sheet directions).

*Note: Only pour sufficient coating to complete the job, replace the lid immediately as exposure to the environment can cause the product quality and performance to be affected. Do not return unused product to the can as this will cause the remaining material to increase in viscosity.*

**Drying:** 30-60 minutes

*Low temperatures and heavy film thickness will retard drying times. Direct sunlight and draft during drying may affect the final gloss level of the coating.*

**Recommended Topcoats:** TITAN Gloss

**Application Equipment Clean Up:** Clean all equipment using Super Cleaning Solvent 3300. Ensure all cleaning solvents are removed before placing equipment back in the coating.

**Shelf Life:** 24 months, see label for use by date. All product must be stored in sealed containers below 25°C. Do not use product is past use by date.

**Packaging:** 20 litres

**Refer to the TITAN Product Information Guide for more information.**

### **Health & Safety**

Before handling, refer to the Material Safety Data Sheet for health and safety information. Ensure that all personnel using this product have read and understood this data sheet and the associated MSDS and packaging label before using this product.

Note: Coatings give off strong solvents and odours during the drying process. People and pets should be removed from the building during the application and drying of coatings. All food and fabrics should also be removed to reduce the risk of them becoming tainted during the drying process.

---

**Mirotone Pty Ltd Australia (Head Office)**

ABN 40 000 041 136

21 Marigold Street, Revesby NSW 2212, Australia, P +61 2 9795 3700 F +61 2 9771 3601

sales@mirotone.com.au

[www.polycure.com.au](http://www.polycure.com.au)